

EXCENOL

Polyols for CASE application

Product	Functionality	Average MW	OH Value (mgKOH/g)	Acid Value (mgKOH/g)	Water Content (%)	pH	Color APHA	Viscosity (25°C) (mPa·s at 25°C)
420	2	400	280	<0.03	<0.05	6.9	10	70
720	2	700	160	<0.05	<0.04	6.6	10	100
1020	2	1,000	112	<0.03	<0.05	6.4	10	150
2020	2	2,000	56	<0.03	<0.03	6.6	10	310
3020	2	3,200	35	<0.03	<0.03	6.6	10	580
510	2	4,000	28	<0.05	<0.05	6.6	20	880
430	3	430	400	<0.05	<0.10	6.6	10	350
1030	3	1,000	160	<0.05	<0.05	6.6	10	250
4030	3	4,000	42	<0.05	<0.05	6.7	10	670
5030	3	5,100	33	<0.03	<0.04	6.6	10	910
230	3	3,000	56	<0.05	<0.05	6.7	10	510
240	3	3,000	56	<0.05	<0.05	6.7	10	500
820	3	4,900	34	<0.05	<0.06	6.9	10	850
823	3	5,100	33	<0.05	<0.05	7.0	20	910
828	3	5,000	34	<0.03	<0.05	6.7	10	890
837	3	6,000	28	<0.05	<0.05	7.4	20	1,200
851	3	6,700	25	<0.05	<0.05	6.7	20	1,300
385SO	6	500	385	<0.05	<0.10	7.0	40	8,500
500ED	4	450	500	-	<0.10	11.0	G-1	6,200
410NE	4	550	410	<0.05	<0.10	6.4	20	1,700

The above technical data is correct at time of going to print: October 2012.

Please contact AGC for further updates and the latest information.

AGC reserves the right to revise its product range at any time without prior notice.

AGC CHEMICALS ASIA PACIFIC PTE

460 Alexandra Road #30-02
PSA Building
Singapore 119963

Tel: +65-6273-5656
Fax: +65-6276-8783
Email : info-agchp@agc.com
www.agc.com/english/

AGC CHEMICALS AMERICAS, INC.

55 East Uwchlan Avenue,
Suite 201, Exton PA 19341
USA

Tel: +1-800-424-7833
Fax: +1-610-423-4301
Email : info-agcchem.com
www.agcchem.com

AGC CHEMICALS EUROPE, LTD.

Commercial Centre
Zuidplein 80
1077 VX Amsterdam, The Netherlands

Tel: +31 (0) 20 880 4170
Fax: +31 (0) 20 880 4188
Email : enquiries@agcce.com
www.agcce.com

EXCENOL

Polyols for CASE application

Product	Structure Outline				Applications										
	Functionality	M.W	OH Value	EO additio	Roofing	Flooring	grout	Sealant	Adhesive	Elastomer	TPU	Coating	Synthetic	RIM	Emulsion
420	2	400	280	NO											
720	2	700	160	NO											
1020	2	1,000	112	NO											
2020	2	2,000	56	NO											
3020	2	3,200	35	NO											
510	2	4,000	28	Yes											
430	3	430	400	NO											
1030	3	1,000	160	NO											
4030	3	4,000	42	NO											
5030	3	5,100	33	NO											
230	3	3,000	56	Yes											
240	3	3,000	56	Yes											
820	3	4,900	34	Yes											
823	3	5,100	33	Yes											
828	3	5,000	34	Yes											
837	3	6,000	28	Yes											
851	3	6,700	25	Yes											
385SO	6	500	385	NO											
500ED	4	450	500	NO											
410NE	4	550	410	NO											

The above technical data is correct at time of going to print: October 2012.
 Please contact AGC for further updates and the latest information.
 AGC reserves the right to revise its product range at any time without prior notice.

AGC CHEMICALS ASIA PACIFIC PTE
 460 Alexandra Road #30-02
 PSA Building
 Singapore 119963

Tel: +65-6273-5656
 Fax: +65-6276-8783
 Email : info-agchp@agc.com
www.agc.com/english/

AGC CHEMICALS AMERICAS, INC.
 55 East Uwchlan Avenue,
 Suite 201, Exton PA 19341
 USA

Tel: +1-800-424-7833
 Fax: +1-610-423-4301
 Email : info-agcchem.com
www.agcchem.com

AGC CHEMICALS EUROPE, LTD.
 Commercial Centre
 Zuidplein 80
 1077 VX Amsterdam, The Netherlands

Tel: +31 (0) 20 880 4170
 Fax: +31 (0) 20 880 4188
 Email : enquiries@agcce.com
www.agcce.com